

BEST AVAILABLE COPY

OCT 13 2006

Attorney's Docket: 2003DE444

Serial No.: 10/735,490


Art Unit: 1714

Response to Restriction Requirement, Dated 10/03/2006


This listing of claims will replace all prior versions, and listings, of claims in the application:

1.(Previously Presented) A fuel oil comprising a proportion of middle distillate having a sulfur content of at most 350 ppm and an aromatics content of at most 22% by weight, and a proportion of at least one copolymer of ethylene and vinyl esters, said copolymer comprising comonomers

a) bivalent structural units derived from ethylene of the formula 1




b) from 5 to 12 mol% of bivalent structural units of the formula 2



where R¹ is saturated, branched C₅-C₁₈-alkyl, and

c) from 4 to 13 mol% of bivalent structural units of the formula 3



2

Attorney's Docket: 2003DE444Serial No.: 10/735,490Art Unit 1714Response to Restriction Requirement, Dated 10/03/2006

wherein a sum of molar proportion of comonomers b) and c) is between 12 and 16 mol%.

2.(Previously Presented)) The fuel oil of claim 1, wherein the molar proportion of the comonomer b) is between 5 and 11 mol%.

3.(Previously Presented) The fuel oil of claim 1, wherein the molar proportion of comonomer c) is between 4.6 and 9 mol%.

4.(Previously Presented) The fuel oil of claim 1, wherein the comonomer b) is a vinyl ester of branched carboxylic acids having from 5 to 15 carbon atoms.

5.(Previously Presented) The fuel oil of claim 1, wherein the copolymer further comprises up to 5 mol% of a further comonomer selected from the group consisting of olefins having from 3 to 18 carbon atoms, esters of acrylic acid or methacrylic acid with C₁-C₁₈-alcohols, C₁-C₁₈-alkyl vinyl ethers, and mixtures thereof.

6.(Previously Presented) The fuel oil of claim 1, wherein the copolymer has a molecular weight (by GPC against poly(styrene)) of from 3000 to 15 000 g/mol.

Attorney's Docket: 2003DE444Serial No.: 10/735,490Art Unit: 1714Response to Restriction Requirement, Dated 10/03/2006

7.(Previously Presented) The fuel oil of claim 1, wherein the copolymer has a degree of branching determined by means of NMR between 2 and 9 CH₃/100 CH₂ groups, not taking into account the methyl groups of the comonomers.

8.(Previously Presented) The fuel oil of claim 1, wherein the copolymers have a melt viscosity at 140°C of from 20 to 10 000 mPas.

9.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate has an aromatic content below 18% by weight.

10.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate has a 90-20% boiling range of less than 110°C.

11.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate has a paraffin content by DSC of more than 3% by weight of precipitated paraffins at 10°C below the cloud point.

12.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate has a density of less than 0.840 g/cm³.

13.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate additionally comprises at least one further ethylene-vinyl ester copolymer.

Attorney's Docket: 2003DE444Serial No.: 10/735,490Art Unit 1714Response to Restriction Requirement, Dated 10/03/2006

14.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate additionally comprises at least one polar nitrogen compound.

15.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate additionally comprises at least one alkylphenol-aldehyde resin.

16.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate additionally comprises at least one comb polymer.


17.(Previously Presented) The fuel oil of claim 1, wherein the middle distillate additionally comprises at least one polyoxyalkylene derivative.

18.(Withdrawn) A copolymer of ethylene and vinyl esters comprising comonomers

a) bivalent structural units derived from ethylene of the formula 1




b) from 5 to 12 mol% of bivalent structural units of the formula 2



Attorney's Docket: 2003DE444Serial No.: 10/735,490Art Unit 1714Response to Restriction Requirement, Dated 10/03/2006

where R¹ is saturated, branched C₈-C₁₈-alkyl, and


- c) from 4 to 13 mol% of bivalent structural units of the formula 3




wherein a sum of molar proportions of structural units of the formulae 2 and 3 is between 12 and 16 mol%.

19.(Currently Amended) A method for improving the cold flow behavior of a middle distillate, said method comprising adding to said middle distillate having a sulfur content of at most 350 ppm and an aromatics content of at most 22% by weight [[said]] of a copolymer of ethylene and vinyl esters comprising comonomers

- a) bivalent structural units derived from ethylene of the formula 1



- b) from 5 to 12 mol% of bivalent structural units of the formula 2



Attorney's Docket: 2003DE444


Serial No.: 10/735,490

Art Unit 1714

Response to Restriction Requirement, Dated 10/03/2006

where R¹ is saturated, branched C₅-C₁₈-alkyl, and

c) from 4 to 13 mol% of bivalent structural units of the formula 3



wherein a sum of molar proportions of structural units of the formulae 2 and 3 is between 12 and 16 mol% of claim 18.

20.(Previously Presented) The method of claim 19, wherein the molar proportion of the comonomer b) is between 5 and 11 mol%.

21.(Previously Presented) The method of claim 19, wherein the molar proportion of comonomer c) is between 4.6 and 9 mol%.

22.(Previously Presented) The method of claim 19, wherein the comonomer b) is a vinyl ester of branched carboxylic acids having from 5 to 15 carbon atoms.

23.(Previously Presented) The method of claim 19, wherein the copolymer further comprises up to 5 mol% of a further comonomer selected from the group consisting of olefins having from 3 to 18 carbon atoms, esters of acrylic acid or methacrylic acid with C₁-C₁₈-alcohols, C₁-C₁₈-alkyl vinyl ethers, and mixtures thereof.

24.(Previously Presented) The method of claim 19, wherein the copolymer has a molecular weight (by GPC against poly(styrene)) of from 3000 to 15 000 g/mol.

Attorney's Docket: 2003DE444Serial No.: 10/735,490Art Unit 1714Response to Restriction Requirement, Dated 10/03/2006

25.(Previously Presented) The method of claim 19, wherein the copolymer has a degree of branching determined by means of NMR between 2 and 9 CH₃/100 CH₂ groups, not taking into account the methyl groups of the comonomers.

26.(Previously Presented) The method of claim 19, wherein the copolymer has a melt viscosity at 140°C of from 20 to 10 000 mPas.

27.(Previously Presented) The method of claim 19, wherein the aromatic content in the middle distillate is below 18% by weight.

28.(Previously Presented) The method of claim 19, wherein the middle distillate has a 90-20% boiling range of less than 110°C.

29.(Previously Presented) The method of claim 19, wherein the middle distillate has a paraffin content by DSC of more than 3% by weight of precipitated paraffins at 10°C below the cloud point.

30.(Previously Presented) The method of claim 19, wherein the middle distillate has a density of less than 0.840 g/cm³.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.